

Diamond Stone Finishing Process

Shaping & Leveling	Natural Granite And Marble	Engineered Stone
<p>GRIND EDGES WITH DIAMOND CUP WHEEL</p> <p>CONTINUE SHAPING WITH 36 GRIT STONE</p> <p>CONTINUE SHAPING WITH 80 GRIT STONE OR</p> <p>30 GRIT TORNADO PAD 50 GRIT TORNADO PAD 100 GRIT TORNADO PAD (USE FIRM BACK VELCRO PAD)</p>	<p>CONTINUE SANDING WITH THE FOLLOWING DIAMOND POLISHING PADS</p> <p>50 GRIT DIAMOND PAD 100 GRIT DIAMOND PAD (Above not needed if using Tornados) 200 GRIT DIAMOND PAD 400 GRIT DIAMOND PAD 800 GRIT DIAMOND PAD 1500 GRIT DIAMOND PAD 3000 GRIT DIAMOND PAD LIGHT OR DARK BUFF PAD</p>	<p>CONTINUE SANDING WITH SOFT RESIN DIAMOND PADS</p> <p>50 GRIT DIAMOND PAD 80 GRIT DIAMOND PAD 100 GRIT DIAMOND PAD (Above not needed if using Tornados) 150 GRIT DIAMOND PAD 300 GRIT DIAMOND PAD 500 GRIT DIAMOND PAD 1000 GRIT DIAMOND PAD 2000 GRIT DIAMOND PAD NO BUFF REQUIRED</p>